



Shade Variation Not Provided
By Manufacturer

PARC

Regularity Characteristics

Technical Features	Norms	Required Standards	Value
Length & Width	ISO 10545-2	Not Provided by Manufacturer	0,1%
Thickness		Not Provided by Manufacturer	3,0%
Straightness of Sides		Not Provided by Manufacturer	0,0%
Rectangularity		Not Provided by Manufacturer	0,3%
Surface Flatness		Not Provided by Manufacturer	0,2% 0,1% 0,2%

Structural Characteristics

Technical Features	Norms	Required Standards	Value
Water Absorption	ISO 10545-3	Not Provided by Manufacturer	0,7% 0,8%

Bulk Mechanical Characteristics

Technical Features	Norms	Required Standards	Value
Breaking Strength	ISO 10545-4	Not Provided by Manufacturer	2515 N Stream 2057 N
Modulus of Rupture		Not Provided by Manufacturer	44.2 N/mm ² Stream 41.2 N/mm ²

Surface Mechanical Characteristics

Technical Features	Norms	Required Standards	Value
Mohs Hardness	EN 101	Not Provided by Manufacturer	7
Resistance to Deep Abrasion	ISO 10545-6	Not Provided by Manufacturer	≤ 140 mm ³

Thermal and Hygrometric Characteristics

Technical Features	Norms	Required Standards	Value
Coefficient of Thermal Linear Expansion	ISO 10545-8	Not Provided by Manufacturer	6.55(10 ⁻⁶ /C°)
Thermal Shock Resistance	ISO 10545-9	Not Provided by Manufacturer	Resistant
Resistance to Frost	ISO 10545-12	Not Provided by Manufacturer	Resistant

Safety Characteristics

Technical Features	Norms	Required Standards	Matte	Brushed	Polished	Stream
Slip Resistance (Pendulum Testers)	A5/NZ 4586-2004	Not Provided by Manufacturer	Wet 42° X	Wet:47° - W	Rockface Wet:41° - X	Wet: 47° - W
Static Coefficient of Friction	ASTM C 1028 (S.C.O.F.)	Not Provided by Manufacturer	≥ 0,77 DRY ≥ 0,67 WET	≥ 0,91 DRY ≥ 0,75 WET	≥ 0,76 DRY ≥ 0,45 WET	≥ 0,77 DRY ≥ 0,67 WET
Non-Slip Classification	DIN 51130	Not Provided by Manufacturer	R10	R11	Rockface R11	R12

Chemical Characteristics

Technical Features	Norms	Required Standards	Value
Resistance to High and Low Concentrations of Acids and Alkalis	ISO 10545-13	Not Provided by Manufacturer	UA ULA/UJC UHA/UHC
Resistance to Staining	ISO 10545-14	Not Provided by Manufacturer	5 Matte: Class A / Polished: Class B

Stocked Sizes (Nominal)

Dimensions	Available Colors
12"x24" Field Tile	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Brushed, Matte, Polished)
24"x24" Field Tile	Ash Grey, Botticino, Crema Luna, Noce, Olive, Sand Beige, Steel Grey (Matte)
4"x12" Bullnose	Ash Grey, Botticino, Charcoal Black, Chocolate, Crema Luna, Noce, Olive, Sand Beige, Steel Grey (Matte, Polished)
12"x36" 3D Bloom	Ash Grey, Crema Luna, Latte, Steel Grey
6"x24" Airstrip Matte/Gloss/Polished Mix	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey
6"x24" Cultural Brick Mosaic	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Matte)
12"x12" Bluetooth Mosaic	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Random)
10 3/8"x12" Hexagon Mosaic	Ash Grey, Crema Luna, Olive, Steel Grey (Matte)
2x2" on 12"x12" Mosaic	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Matte)
2x4" on 12"x12" Mosaic	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Matte)

Special Order Sizes* (Nominal)

Dimensions	Available Colors
12"x12" Field Tile	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Matte, Polished)
6"x6", 24"x2", 24"x4", 24"x6" Field Tile	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Brushed, Matte, Polished)
20 3/8"x24" Hexagon	Ash Grey, Crema Luna, Olive, Steel Grey (Matte)
24"x4", 12"x4" Bullnose, Square	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Matte, Polished)
24"x12", 12"x12" Gradino, Gradino Tread	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Matte, Polished)
12"x4"x2", 12"x4"x1" Cove	Ash Grey, Botticino, Concrete, Crema Luna, Latte, Noce, Olive, Sand Beige, Steel Grey (Matte)

* 12 - 14 Week Lead Time

Recycled Content

Not Provided By Manufacturer