



Cream


Greige

Moka



Pearl

White



V2 Slight Variation

SIGN

Regularity Characteristics

Technical Features	Norms	Required Standards			Floor	
		7 cm ≤ N < 15 cm	N ≥ 15 cm		Matte	Brushed
Length & Width		± 0,9mm*	± 0,6%*	± 0,2mm*	Suitable for	Suitable for
Thickness		± 0,5mm**	± 5%**	± 0,5mm**	± 5% ± 0,5mm	± 5% ± 0,5mm
Straightness of Sides	ISO 10545-2	± 0,75mm***	± 0,5%***	± 1,5mm***	Suitable for	Suitable for
Rectangularity		± 0,75mm****	± 0,5%****	± 2mm****	Suitable for	Suitable for
Surface Flatness		c.c. ± 0,75mm e.c. ± 0,75mm w ± 0,75mm	c.c. ± 0,5% e.c. ± 0,5% w ± 0,5%	c.c. ± 2mm e.c. ± 2mm w ± 2mm	± 0,3% ± 1,3mm	± 0,3% ± 1,3mm

Structural Characteristics

Technical Features	Norms	EN 14411 annex G	ISO 13006 annex G	Matte	Brushed
Water Absorption	ISO 10545-3	E _B ≤ 0,5% Individual Maximum 0,6%		≤ 0,1%	≤ 0,1%

Bulk Mechanical Characteristics

Technical Features	Norms	EN 14411 annex G	ISO 13006 annex G	Matte	Brushed
Breaking Strength	ISO 10545-4	S ≥ 1300 N		S ≥ 1500 N	S ≥ 1500 N
Modulus of Rupture		R ≥ 35 N/mm ²		R ≥ 40 N/mm ²	R ≥ 40 N/mm ²

Surface Mechanical Characteristics

Technical Features	Norms	EN 14411 annex G	ISO 13006 annex G	Matte	Brushed
Mohs Hardness	EN 101	≥ 6		Suitable for	Suitable for
Impact resistance	ISO 10545-5	Declared value	Test method available	≥ 0,55	≥ 0,55
Resistance to Deep Abrasion	ISO 10545-6	≤ 175 mm ³		≤ 150 mm ³	≤ 150 mm ³

Thermal and Hygrometric Characteristics

Technical Features	Norms	EN 14411 annex G	ISO 13006 annex G	Matte	Brushed
Coefficient of Thermal Linear Expansion	ISO 10545-8	Declared value	Test method available	≤ 7 MK ⁻¹	≤ 7 MK ⁻¹
Thermal Shock Resistance	ISO 10545-9	Test Method Available	Test method available	Resistant	Resistant
Moisture expansion	ISO 10545-10	Declared value	Test method available	≤ 0,01%	≤ 0,01%
Resistance to Frost	ISO 10545-12	Pass according to ISO 10545-1	Test method available	Resistant	Resistant

Safety Characteristics

Technical Features	Norms	EN 14411 annex G	ISO 13006 annex G	Matte	Brushed
Dynamic Friction Coefficient	ANSI A137.1-2012 (D.C.O.F.)	≥ 0,42 WET		≥ 0,42 WET	-
Static coefficient of friction	ASTM C1028-2007 (S.C.O.F.)	Slip Resistant (≥ 0,60)		≥ 0,60 DRY ≥ 0,60 WET	≥ 0,60 DRY ≥ 0,60 WET
Shod Ramp Test	DIN 51130	Declared value		R9	R9
Barefoot Ramp Test	DIN 51097	Declared value		A	A
Pendulum Friction Test	UNE-ENV 12633	Declared value		Class 1	Class 1
	BS 7976-2002	Declared value		PTV > 36 Dry PTV < 25 Wet	PTV > 36 Dry PTV < 25 Wet

Chemical Characteristics

Technical Features	Norms	EN 14411 annex G	ISO 13006 annex G	Matte	Brushed
Resistance to Household Chemicals and Swimming Pool Salts	ISO 10545-13	Class B (U for unglazed tiles) min.		UA	UA
Resistance to low Concentrations of Acids and Alkalis		Declared value	Test Method Available	UA	UA
Resistance to High Concentrations of Acids and Alkalis		Declared value	Test Method Available	UHA	UHA
Resistance to Staining	ISO 10545-14	Minimum Class 3		5	5

Stocked Sizes (Nominal)


Dimensions	Available Colors
8x20"x8mm Ceramic Field Tile	Cream, Greige, Moka, Pearl, White (Shiny)
12x24"x9mm Field Tile	Cream, Greige, Moka, Pearl, White (Matte)
3x24" Bullnose	Cream, Greige, Moka, Pearl, White (Matte)
12x12" Mosaico	Cream, Greige, Moka, Pearl, White (Matte)

Special Order Sizes* (Nominal)

Dimensions	Available Colors
45x45 - 17 3/4"x17 3/4" Field Tile 	Cream, Greige, Moka, Pearl, White
20x50 - 7 7/8"x19 1/8" Wave Decor (Wall) 	Cream, Pearl, White
20x50 - 7 7/8"x19 1/8" Geo Decor (Wall) 	Pearl, White, Multi
15x30 - 5 7/8"x11 1/4" Cove Base 	Cream, Greige, Moka, Pearl, White
30x60 - 11 3/4"x23 1/8" Gradino 	Cream, Greige, Moka, Pearl, White

* 12 - 14 Week Lead Time

Recycled Content

 20% - Greige 18x18" & 12x24", 40% - Moka 18x18" & 12x24"

FLOOR

WALL

COUNTERTOP